

521,795

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
5 February 2004 (05.02.2004)

PCT

(10) International Publication Number
WO 2004/011717 A1

- (51) International Patent Classification⁷: **D21C 5/02**, (74) Agents: **WILLIAMS, Paul, Edwin et al.**; Ablett & Stebbing, Caparo House, 101-103 Baker Street, London W1U 6FQ (GB).
- (21) International Application Number: **PCT/EP2003/008166** (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (22) International Filing Date: **22 July 2003 (22.07.2003)**
- (25) Filing Language: **English**
- (26) Publication Language: **English**
- (30) Priority Data: **0217197.3** **24 July 2002 (24.07.2002)** **GB** (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (71) Applicants (*for all designated States except US*): **DOW CORNING CORPORATION** [US/US]; Midland, MI 48611 (US). **NOPCO PAPER TECHNOLOGY GMBH** [DE/DE]; Marbacher Strasse 114, 40597 Dusseldorf (DE).
- (71) Applicant (*for US only*): **NORTHFLEET, Christina** [DE/BE]; 6 Montagne au Chaudron, B-1150 Brussels (BE).
- (72) Inventor; and
- (75) Inventor/Applicant (*for US only*): **NELLESSEN, Bernhard** [DE/DE]; Alma-Mahler-Werfel-Strasse 4, 41564 Kaarst (DE).
- Published:
— with international search report
— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **METHOD OF DEINKING**

(57) Abstract: A method of deinking printed paper comprises pulping the paper to form an aqueous slurry, adding a deinking additive to the paper, and removing detached ink by flotation, wherein the additive comprises an organo-modified siloxane comprising units of the formula: $[R^1_n Z_b SiO_{(4-a-b)_2}]_n$ in which each R^1 is independently selected from a hydrogen atom, an alkyl, aryl, alkenyl, aralkyl, alkaryl, alkoxy, alkanoyloxy, hydroxyl, ester or ether group; each Z is independently selected from an alkyl group substituted with an amine, amide, carboxyl, ester, or epoxy group, or a group $-R^2-(OC_p H_{2p})_q (OC_r H_{2r})_s R^3$; n is an integer greater than 1; a and b are independently 0, 1, 2 or 3; R^2 is an alkylene group or a direct bond; R^3 is a group as defined for R^1 or Z above; p and r are independently an integer from 1 to 6; q and s are independently 0 or an integer such that $1 \leq q + s \leq 400$; and wherein each molecule of the organo-modified siloxane contains at least one group Z .



WO 2004/011717 A1

- 1 -

METHOD OF DEINKING

The present invention relates to a method of deinking printed wastepaper.

5 Growing awareness of environmental damage caused by deforestation has seen an increase in the recycling of wastepaper in recent years. It has been recognised that the ability to recycle wastepaper is commercially advantageous and has a significant impact on the conservation of virgin fibre
10 resources. However, technological advances in printing inks and print media present ever-growing challenges to recyclers.

Printing on paper is typically accomplished using one of two types of ink, namely, impact ink, which is physically pressed onto the paper, and non-impact ink, which is attracted
15 to a charged image and is then transferred to the paper. Impact inks are typically wet inks, for example letterpress inks, offset litho inks, photogravure inks and flexographic inks. For example, letterpress inks are generally composed of carbon black pigment in a mineral oil vehicle and are used
20 in, for example, newspaper printing. Offset litho inks tend to contain more pigment than letterpress inks and contain drying oils such as linseed or alkyl resins. Flexographic inks are used in similar processes to letterpress inks but are water-based and contain emulsified ink in an alkali soluble
25 binder. Such inks may easily be dislodged, but may form extremely fine particles that are difficult to capture and remove.

Non-impact inks, e.g. toners, are generally dry, powdered inks and are used in laser printing, photocopying and
30 facsimile machines and generally comprise thermoplastic resins and pigment.

The deinking of paper bearing these two different types of ink requires different deinking procedures and conditions.

CONFIRMATION COPY

- 2 -

Conventionally, deinking of paper bearing non-impact ink merely requires pulping with a surfactant in neutral conditions, whereas paper bearing impact ink requires different conditions, such as treatment with alkali, silicate and peroxide, as well as a surfactant.

In conventional deinking methods, the wastepaper is disintegrated (pulped) by mechanical agitation in an aqueous medium to separate the ink and impurities from the paper fibre and disintegrate the ink into particles of approximately 0.1 to 1000 μm . A grey slurry is thus obtained in which the ink is present in a finely dispersed form. The impurities, for example, plastic, aluminium foil, stones, screws, staples, paper clips etc., are removed during a large number of screening steps.

Whilst ink detachment of non-impact, e.g. photocopy, paper can normally be achieved in neutral conditions, for other printed paper ink detachment is routinely accomplished at alkaline pH levels using alkali hydroxides, alkali silicates, oxidative-working bleaches and surfactants at temperatures between 30 and 50°C. Usually, anionic and nonionic tensides are used as surfactants, for example, soaps, ethoxylated fatty alcohols and/or ethoxylated alkyl phenols (see, for example, EP 0013758).

The ink particles are then removed from the fibre slurry by washing and/or flotation. Smaller ink particles are removed by washing, and larger ink particles and stickies (i.e. glue residues and adhesives) are removed by flotation. During flotation, air bubbles are blown into the pulp. The dispersed ink particles become attached to the air bubbles, which carry the ink particles to the surface. The resultant foam is then skimmed from the surface. Subsequent steps involve heating the pulp to evenly distribute stubborn ink particles and screening the pulp to separate the damaged,

- 3 -

short or weak fibres. The remaining clean pulp is then pressed between rollers into sheets and dried.


Thus, efficient deinking demands both successful separation of the ink from the paper fibre and removal of the dispersed ink from the fibre slurry.

However, there are a number of disadvantages associated with traditional deinking methods. For example, the incomplete removal of ink particles from the fibre slurry can cause the resulting paper to have a grey hue, spotting, and a low degree of brightness. Brightness and colour are important quality criteria for many paper uses.

In addition, the alkaline conditions used in traditional deinking methods cause water-soluble and/or colloidal solids and finely dispersed solids to contaminate the process water, for example, fillers, fine fibres and stickies. If these contaminants are insufficiently removed during washing, they can be concentrated by subsequent washings and reintroduced to the paper fibre, causing a loss of brightness in the resultant paper. Effluent containing the aforementioned chemicals conventionally used in deinking methods is also environmentally undesirable.

The present invention seeks to provide a method of deinking wastepaper which can overcome disadvantages of conventional deinking methods.

According to the present invention there is provided a method of deinking printed paper, the method comprising pulping the paper to form an aqueous slurry, adding a deinking additive to the paper, and removing detached ink by flotation, wherein the additive comprises an organo-modified siloxane comprising units of the formula:



- 4 -

in which each R^1 is independently selected from a hydrogen atom, an alkyl, aryl, alkenyl, aralkyl, alkaryl, alkoxy, alkanoyloxy, hydroxyl, ester or ether group;

each Z is independently selected from an alkyl group substituted with an amine, amide, carboxyl, ester, or epoxy group, or a group $-R^2-(OC_pH_{2p})_q(OC_rH_{2r})_s-R^3$;

n is an integer greater than 1;

a and b are independently 0, 1, 2 or 3;

R^2 is an alkylene group or a direct bond;

10 R^3 is a group as defined for R^1 or Z above;

p and r are independently an integer from 1 to 6;

q and s are independently 0 or an integer such that $1 \leq q + s \leq 400$;

and wherein each molecule of the organo-modified siloxane contains at least one group Z.

Z is preferably a group $-R^2-(OC_pH_{2p})_q(OC_rH_{2r})_s-R^3$, more preferably wherein p and/or r are independently 2, 3 or 4, i.e. a group comprising ethylene, propylene, and/or butylene oxide groups. Preferably, q and s are each independently 20 integers from 10 to 30, more preferably 15 to 25 (for example 18). In a particularly preferred group Z, p is 2, r is 3, and q and s are both 18. R^2 may be an alkylene group, for example having from 1 to 6 carbon atoms (i.e. a methylene, ethylene, propylene, butylene, pentylene or hexylene group), or a direct 25 bond. R^3 may be a group as defined hereinabove for R^1 or Z, and is preferably a hydrogen atom or a hydroxyl group.

Additionally or alternatively, Z may be an alkyl group substituted with an amine, amide, carboxyl, ester, or epoxy group, for example an alkyl group having from 1 to 6 carbon 30 atoms, i.e. a substituted methyl, ethyl, propyl, butyl, pentyl or hexyl group.

The siloxane may be linear or may comprise units in which $a + b = 0$ or 1, i.e. the siloxane may contain branching. When

- 5 -

Z is a group $-R^2-(OC_pH_{2p})_q(OC_rH_{2r})_s-R^3$, R^3 is preferably a hydroxyl or alkanoyloxy group.

Preferably, 2 to 20 mole percent of silicon atoms in the siloxane molecule are substituted by a group Z, more preferably 5 to 16 mole percent.

The siloxane preferably has a hydrophilic/lipophilic balance (HLB) in the range of 5.0 to 7.3.

The molecular weight of the siloxane is preferably in the range of 1,000 to 500,000, more preferably 10,000 to 100,000.

10 A particularly preferred siloxane for use in the present invention is a hydroxy-endcapped linear polydimethylsiloxane having an HLB of 5.9 to 6.3, in which 10 to 12 mole percent of silicon atoms are substituted by Z groups of the formula $-R^2-(OC_pH_{2p})_q(OC_rH_{2r})_s-R^3$, in which p is 2, r is 3 and q and s are
15 both 18, R^2 is an alkylene group having from 1 to 6 carbon atoms or a direct bond, and R^3 is a hydrogen atom or a hydroxyl, ester or ether group.

The additive used in the present invention may comprise further components, in addition to the organo-modified
20 siloxane. For example, the additive may further comprise one or more components selected from a polydimethylsiloxane, an organic polyether, and a fatty acid. Suitable organic polyethers include those of the formula $R^4-(OC_pH_{2p})_q(OC_rH_{2r})_s-R^5$ in which R^4 and R^5 are selected from a hydrogen atom,
25 hydroxyl, alkyl and alkoxy groups, and p, q, r and s are as defined hereinabove. Suitable fatty acids include saturated and unsaturated monobasic aliphatic carboxylic acids, for example having from 8 to 22 carbon atoms, such as lauric, myristic, palmitic, stearic, arachidic, behenic, lignoceric,
30 palmitolic, oleic, linoleic, linolenic, and arachidonic acids.

The additive may be in the form of an emulsion, for example the organo-modified siloxane may be a gum based self-emulsifying siloxane.

- 6 -

In the method of the present invention, the additive may be added to the paper before, during or after pulping. The amount of additive to be added to the paper is preferably within the range 0.1 to 1 wt% of the paper, more preferably 0.1 to 0.5 wt%. The additive may, for example, be added to the paper neat, as an emulsion, or in solution, for example an aqueous solution.

The method of the present invention is preferably performed at substantially neutral pH, although the method may be performed under alkaline pH.

The pulping and ink removal steps of the present invention may be performed as is conventional, as will be familiar to a person skilled in the art and described hereinabove. For example, the paper may be pulped to form an aqueous slurry having a consistency of, for example, from 1 to 10% (for example, 1 to 5%) at a temperature of between 30 and 50°C, for example 35 to 45°C. Consistency is defined as wt% of pulp solids in the fibre suspension. Ink removal may be performed in a suitable flotation cell (for example, a Denver Lab flotation cell) at a suitable temperature, for example between 30 and 50°C (e.g. 35 to 45°C), and number of revolutions per minute, for example from 500 to 1000 rpm. An additional advantage associated with the method of the present invention is that when used to treat flexographic printed waste, the process water is relatively clear, whereas with known deinking methods it is generally black. Moreover, the present method produces pulp of improved brightness.

Embodiments of the present invention will now be described in detail.

30

Example 1

a) Pulping

To an aqueous suspension of 110g of air-dry wastepaper

- 7 -

(50% newspaper and 50% magazine paper) having a consistency of 4% were added 440g of industrial water at 45°C in a mixing vessel. The suspended paper was kneaded for 15 minutes at 45°C.

5 b) Ink removal

Water having a hardness of 16°dH was added to the pulp obtained in a) above to achieve a consistency of 1%. To the pulp varying amounts of a hydroxyl endcapped polydimethylsiloxane having approximately 11 mole % silicon
10 atom substitution by $-(OC_2H_4)_{18}(OC_3H_6)_{18}$ side chains, an HLB of approximately 6.1 and a molecular weight of approximately 60,000 (referred to herein as Siloxane 1) was added as an aqueous solution. The pulp was floated for 8 minutes at 45°C in a Denver Lab Flotation Cell at 1000 rpm, after which the
15 pulp was separated from the water, and formed into sheets between two filters of a sheet former with drying at 95°C for 10 minutes under vacuum.

By way of comparison, steps a) and b) above were repeated using a commercially available fatty acid based deinking
20 preparation. The results are shown in Table 1 below. Whiteness was evaluated according to DIN 53145 Part 1.

Table 1

Additive	wt % of additive used	Paper	pH	Whiteness before flotation %	Whiteness after flotation %	Whiteness difference %
Fatty acid	0.4	aged	8.5	42.4	59.0	16.6
Fatty acid	0.4	fresh	7.2	43.6	51.3	7.7
Siloxane 1	0.3	aged	8.5	46.6	61.9	15.3
Siloxane 1	0.3	fresh	8.5	46.6	61.9	15.3
Siloxane 1	0.3	fresh	7.2	46.5	59.1	12.6
Siloxane 1	0.1	fresh	7.2	44.6	56.5	11.9
Siloxane 1	0.3	aged	7.2	40.2	47.8	7.6

Example 2a) Pulping

To an aqueous suspension of 110g of air-dry wastepaper (10% newspaper and 90% magazine paper) having a consistency of 20% were added 440ml of industrial water at 45°C in a mixing vessel. The suspended paper was kneaded for 15 minutes at 45°C.

b) Ink removal

Water was added to the pulp obtained in a) above to achieve a consistency of 1.09%. To the pulp varying amounts of a hydroxyl endcapped siloxane as defined in Table 4 below were added as an aqueous solution. The pulp was floated for 8 minutes at 45°C in a Denver Lab Flotation Cell.

Steps a) and b) above were repeated using the siloxane used in Example 1 (Siloxane 1) and the siloxanes defined in Table 4 (Siloxanes 2 to 8) on fresh and aged wastepaper. Table 4 also contains viscosity data for each of the siloxanes. By way of comparison, the experiment was also carried out using the commercially available fatty acid based deinking preparation used in Example 1. The results are shown in Table 2 (fresh wastepaper) and Table 3 (aged wastepaper) below. Whiteness was evaluated according to DIN 53145 Part 1.

Table 2

Additive	wt % of additive used	pH	Whiteness before flotation %	Whiteness after flotation %	Whiteness difference %
Fatty acid	0.4	8.1	35.8	51.1	15.3
Siloxane 1	0.3	7.5	39.4	56.5	17.1
Siloxane 2	0.3	7.5	39.1	54.2	15.1
Siloxane 3	0.3	7.5	40.2	55.0	14.8
Siloxane 4	0.3	7.5	37.8	55.0	17.2
Siloxane 5	0.3	7.5	39.0	52.6	13.6
Siloxane 6	0.3	7.5	41.2	53.5	12.3
Siloxane 7	0.3	7.5	39.5	57.1	17.6
Siloxane 8	0.3	7.5	40.1	54.0	13.9

Table 3

Additive	wt % of additive used	pH	Whiteness before flotation %	Whiteness after flotation %	Whiteness difference %
Fatty acid	0.4	7.8	36.3	44.6	8.3
Siloxane 1	0.3	7.3	37.0	47.8	10.8
Siloxane 4	0.3	7.3	37.0	50.3	13.3
Siloxane 7	0.3	7.3	37.5	48.0	10.5

5

Table 4

n (degree of polymerisation)	% Substituted Silicon atoms		
	5	10	15
100	Siloxane 2 7,720 cP	Siloxane 3 5,560 cP	Siloxane 4 3,100 cP
300	Siloxane 5 98,540 cSt	Siloxane 6 6,060 cP	Siloxane 7 5,090 cP
500			Siloxane 8 6,830 cP

10

15

- 12 -

Example 3a) Pulping

To an aqueous suspension of 110g of air-dry wastepaper (100% newspaper) having a consistency of 20% were added 400ml of industrial water at 45°C in a mixing vessel. The suspended paper was kneaded for 15 minutes at 45°C.

b) Ink removal

Water was added to the pulp obtained in a) above to achieve a consistency of 1.09%. To the pulp varying amounts of a hydroxyl endcapped siloxane as defined in Table 4 and Example 1 were added as an aqueous solution. The pulp was floated for 8 minutes at 45°C in a Denver Lab Flotation Cell.

Steps a) and b) above were repeated using the siloxane used in Example 1 (Siloxane 1) and two of the siloxanes defined in Table 4 (Siloxanes 4 and 7). By way of comparison, the experiment was also carried out using the commercially available fatty acid based deinking preparation used in Example 1. The results are shown in Table 5 below. Whiteness was evaluated according to DIN 53145 Part 1.

20

Example 4

Steps a) and b) of Example 1 were repeated using the siloxane used in Example 1 (Siloxane 1), but were performed on 100% flexographic paper. In addition, 0.10 wt% sodium hydroxide and 1.20 wt% sodium silicate were added to the slurry.

By way of comparison, the experiment was also carried out using the commercially available fatty acid based deinking preparation used in Example 1. The results are shown in Table 6 below. The appearance of the filtration water was also recorded. Whiteness was evaluated according to DIN 53145 Part 1.

- 13 -

Table 5

Additive	wt % of additive used	pH	Whiteness before flotation %	Whiteness after flotation %	Whiteness difference %
Fatty acid	0.4	7.7	24.7	27.0	2.3
Siloxane 1	0.3	7.3	26.5	33.0	6.5
Siloxane 4	0.3	7.2	24.4	33.0	8.6
Siloxane 7	0.3	7.3	26.0	35.0	9.0

5

Table 6


Additive	wt % of additive used	Whiteness before flotation %	Whiteness after flotation %	Whiteness difference %	Appearance of filtration water
Fatty acid	0.4	28.8	29.9	1.1	Dark black
Siloxane 1	0.2	25.4	33.4	8.0	Light grey
Siloxane 1	0.2	26.6	34.5	7.9	Light grey

15

- 14 -

CLAIMS

1. A method of deinking printed paper, the method comprising pulping the paper to form an aqueous slurry, adding a deinking additive to the paper, and removing detached ink by flotation, wherein the additive comprises an organo-modified siloxane comprising units of the formula:



10

in which each R^1 is independently selected from a hydrogen atom, an alkyl, aryl, alkenyl, aralkyl, alkaryl, alkoxy, alkanoyloxy, hydroxyl, ester or ether group;

each Z is independently selected from an alkyl group substituted with an amine, amide, carboxyl, ester, or epoxy group, or a group $-R^2-(OC_pH_{2p})_q(OC_rH_{2r})_s-R^3$;

n is an integer greater than 1;

a and b are independently 0, 1, 2 or 3;

R^2 is an alkylene group or a direct bond;

20 R^3 is a group as defined for R^1 or Z above;

p and r are independently an integer from 1 to 6;

q and s are independently 0 or an integer such that $1 \leq q + s \leq 400$;

and wherein each molecule of the organo-modified siloxane contains at least one group Z.

2. A method according to claim 1 wherein Z is a group $-R^2-(OC_pH_{2p})_q(OC_rH_{2r})_s-R^3$.

30 3. A method according to claim 2 wherein p and/or r are independently 2, 3 or 4.

4. A method according to claim 2 or 3 wherein q and s are

- 15 -

each independently integers from 10 to 30.

5. A method according to claim 4 wherein q and s are each independently 15 to 25.

5

6. A method according to any one of claims 2 to 5 wherein p is 2, r is 3, and q and s are both 18.

7. A method according to any preceding claim wherein R² is
10 a methylene, ethylene, propylene, butylene, pentylene or hexylene group.

8. A method according to any preceding claim wherein R³ is a hydrogen atom or a hydroxyl group.

15

9. A method according to any preceding claim wherein the siloxane is linear.

10. A method according to any preceding claim wherein the
20 siloxane contains branching.

11. A method according to any preceding claim wherein Z is a group $-R^2-(OC_pH_{2p})_q(OC_rH_{2r})_s-R^3$, and R³ is a hydroxyl or alkanoyloxy group.

25

12. A method according to any preceding claim wherein 2 to 20 mole percent of silicon atoms in the siloxane molecule are substituted by a group Z.

30 13. A method according to claim 12 wherein 5 to 16 mole percent of silicon atoms in the siloxane molecule are substituted by a group Z.

- 16 -

14. A method according to any preceding claim wherein the siloxane has a hydrophilic/lipophilic balance (HLB) in the range of 5.0 to 7.3.

5 15. A method according to any preceding claim wherein the siloxane has a molecular weight in the range of 1,000 to 500,000.

16. A method according to claim 15 wherein the siloxane has
10 a molecular weight in the range of 10,000 to 100,000.

17. A method according to any preceding claim wherein the siloxane is a hydroxy-endcapped linear polydimethylsiloxane having an HLB of 5.9 to 6.3, in which 10 to 12 mole percent
15 of silicon atoms are substituted by Z groups of the formula $-R^2-(OC_pH_{2p})_q(OC_rH_{2r})_s-R^3$, in which p is 2, r is 3 and q and s are both 18, R^2 is an alkylene group having from 1 to 6 carbon atoms or a direct bond, and R^3 is a hydrogen atom or a hydroxyl, ester or ether group.

20

18. A method according to any preceding claim wherein the additive further comprises one or more components selected from a polydimethylsiloxane, an organic polyether, and a fatty acid.

25

19. A method according to claim 18 wherein the additive further comprises an organic polyether of the formula $R^4-(OC_pH_{2p})_q(OC_rH_{2r})_s-R^5$ in which R^4 and R^5 are selected from a hydrogen atom, hydroxyl, alkyl and alkoxy groups, p and r are
30 independently an integer from 1 to 6, and q and s are independently 0 or an integer such that $1 \leq q + s \leq 400$.

20. A method according to claim 18 or 19 wherein the additive

- 17 -

further comprises a fatty acid which is a saturated or unsaturated monobasic aliphatic carboxylic acid.

21. A method according to claim 20 wherein the carboxylic
5 acid is selected from lauric, myristic, palmitic, stearic, arachidic, behenic, lignoceric, palmitolic, oleic, linoleic, linolenic, and arachidonic acids.

22. A method according to any preceding claim wherein the
10 additive is an emulsion.

23. A method according to claim 22 wherein the additive is a gum based self-emulsifying siloxane.

15 24. A method according to any preceding claim wherein the additive is added to the paper in an amount within the range 0.1 to 1 wt% of the paper.

25 25. A method according to claim 24 wherein the additive is added to the paper in an amount within the range 0.1 to 0.5 wt% of the paper.

26. A method according to any preceding claim which is performed at substantially neutral pH.

25

27. A method substantially as hereinbefore described.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 03/08166

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 D21C5/02 D21H17/13 D21H17/59

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D21C D21H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5 624 569 A (CHUNG DANIEL K ET AL) 29 April 1997 (1997-04-29) abstract; claim 1	1-27
Y	EP 0 745 648 A (DOW CORNING) 4 December 1996 (1996-12-04) page 5, line 50 - line 53 claims 1-9	1-27

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

30 December 2003

Date of mailing of the international search report

12/01/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl
Fax: (+31-70) 340-3016

Authorized officer

Naeslund, P

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 03/08166

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5624569	A	29-04-1997	AT 188491 T	15-01-2000
			AU 711097 B2	07-10-1999
			AU 5699896 A	29-11-1996
			BR 9606364 A	09-09-1997
			CA 2194295 A1	14-11-1996
			DE 69606011 D1	10-02-2000
			EP 0775165 A1	28-05-1997
			WO 9635731 A1	14-11-1996
			JP 10505383 T	26-05-1998
			NO 970053 A	07-03-1997
			PL 318058 A1	12-05-1997
EP 0745648	A	04-12-1996	EP 0745648 A2	04-12-1996
			JP 8323108 A	10-12-1996